



PRECISION EeZeClean Dry Erase Coating

PRECISION COATINGS

Description

Turns a smooth surface into a write & erase space with a dry erase marker
Available in white, clear & custom colors
Standard Sheen: Gloss
Surface ready for use in 5 days
LEED NC 2009 compliant

Two component modified epoxy coating
No ghosting & easily cleaned
Low VOC / Low Odor
Excellent chemical durability
Cures at ambient temperature
Interior / Exterior on appropriate substrates

USE

Precision EeZeClean converts paintable surfaces including walls, columns, panels, hallways and old chalk boards into creative writing / art spaces.

Ideal for offices, schools, hospitals, retail, government and hospitality

TECHNICAL DATA

% SOLIDS by volume	70% as applied
COATINGS VOC (as packaged)	max. 3 g/l (less water & exempt compounds)
SPRAYABLE VOC (as applied)	max. 96 g/l (less water & exempt compounds) includes cure volatiles
COMPONENTS	Advanced Polymer Modified Epoxy Coating Resin 4 parts / Activator 1 part
POT LIFE	4 hours @ 70° F, 21° C
SHELF LIFE	one year (unopened)
REDUCERS	Not required
FLASH POINT	109° F, 42.8° C
MIX RATIO	4:1 (4 parts resin : 1 part activator)
RECOMMENDED DRY FILM THICKNESS	3-5 mils per coat (75-125 microns), 1 to 2 coats
THERORETICAL COVERAGE	401 – 240 sq ft at recommended DFT (theoretical)

SURFACE PREPARATION

Precision EeZeClean Dry Erase may be applied directly over properly prepared substrates (Level 5 smoothness is recommended) including steel, aluminum, galvanizing, concrete, masonry, ceramic tile, MDF, drywall and previously primed or coated surfaces. Good painting practices dictate that before applying this Precision product, a test be performed to ensure that the adhesion, appearance, and color are compatible with the substrate and meet the expectations of the owner.

Steel, Aluminum & Galvanizing– Clean the surface of all foreign material SSPC-SP1 and SSPC-SP2 or SSPC-SP3, 6, or 7. Substrate must be clean and dry prior to application of the Precision EeZeClean Dry Erase. For primed substrates, follow the surface preparation instructions and recoat times for the specific primer used.

Ceramic Tile – Tile surface and grout must be clean and dry. All wax, grease, silicone sealants and dirt must be removed from the surface. It is strongly recommended that a test application be completed on ceramic tile to ensure adhesion prior to commencement of full application of Precision EeZeClean Dry Erase.

Concrete, Masonry, Wood MDF, Drywall, FRP – Surface must be cured, clean, dry, and free of any dirt, dust, grease, oil, wax, mildew, disintegrated or chalky materials or other contaminants. For primed substrates, follow the surface preparation instructions and recoat times for the specific primer used.

Previously Coated surfaces – Physically abrade existing coated surfaces thoroughly and completely with 220 grit or equivalent abrasive paper or scuff pad. . Substrate must be clean and dry prior to application of the Precision EeZeClean Dry Erase For primed substrates, follow the surface preparation instructions and recoat times for the specific primer used.

Use & Maintenance – Use any standard dry erase marker. For best results, use Expo® Bold or low odor dry erase markers. For daily erasing and cleaning, use a clean, dry erase cotton cloth, eraser, or micro-fiber towel. Periodically use a clean damp cloth, dry erase cleaner or isopropyl alcohol.

PRECISION COATINGS

1940 E. Trafficway, Springfield, MO 65802
888.340.6780 or 417.862.5738 fax 417.862.8874
www.precisioncoatingsinc.com



PRECISION EeZeClean Dry Erase

PRECISION COATINGS

INSTRUCTIONS – MIX RATIO

To optimize performance Precision Coatings recommends EeZeClean be applied over a smooth substrate such as a Level 5 wall finish. EeZeClean can be professionally sprayed to optimize finish smoothness.

Stir or drill motor mix thoroughly to ensure uniform mixture. Mix 4 parts EeZeClean Dry Erase Coating with 1 part EeZeClean dry Erase Activator. Additional reduction is not necessary.

APPLICATION

Apply using 40-55 PSI at the gun for siphon and gravity feed spray guns, 10 PSI max. at the air cap for HVLP spray guns. Apply 1-2 medium wet coats until desired coverage and flow is reached. Allow a 5 to 10 minute flash time between coats. Recommended film thickness is 3.0 to 5.0 mils DFT. Surface temperatures must be at least 5° F (3° C) above the dew point for application. Relative humidity below 40 % will extend the dry times.

SPRAY GUN SET-UP & PRESSURE

<u>Type</u>	<u>Fluid Tip</u>	<u>Spraying Pressure</u>
Siphon Feed	1.4mm – 1.7mm	40-65-PSI
Gravity Feed	1.3mm – 1.4mm	40-65 PSI
HVLP Siphon	1.3mm – 1.5mm	max. 10 PSI @ the air cap
HVLP Gravity	1.3mm – 1.5mm	max. 10 PSI @ the air cap
Pressure Pot	1.1 mm- 1.3 mm	29 PSI - 58 PSI
Airless Spray	.015" - .025" (for clears and solid colors only)	

ROLLER AND BRUSH APPLICATION

Brush – natural bristle

Roller – 3/16 to 3/8 inch nap, phenolic core

DRY TIMES

Dry times @ 70°F (21°C) and 50% RH

Tack Free	4 hours
Dry Time	24 hours
Recoat	May be recoated with itself at any stage.

PACKAGING Available in Quart and Gallon Kits

CLEAN UP

Follow local, state and federal regulations. Clean all spray equipment immediately after use. Acetone may be used to clean spray equipment. PCI's 17000 Gun Cleaner is a VOC exempt cleaner and is recommended for cleaning application equipment used to apply the Precision EeZeClean Dry Erase. Refer to Material Safety Data Sheet for proper handling of products listed in this bulletin. Acetone may be used to clean application equipment immediately after use.

Refer to Material Safety Data Sheet for proper handling of products listed in this bulletin.

DISCLAIMER: The technical information and suggestions for use have been compiled for your guidance and usage. Such information is based on experience and research and is believed to be reliable. As the manufacturer has no control over conditions in which the product is used, stored, or otherwise handled, the above information does not constitute a warranty. Buyers must assume responsibility for the suitability of the product for their purposes.

11.2011

PRECISION COATINGS

1940 E. Trafficway, Springfield, MO 65802
888.340.6780 or 417.862.5738 fax 417.862.8874
www.precisioncoatingsinc.com